



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



---

---

TECHNICAL DATA SHEET

---

---

**REFERENCE: OPAK X FR**

**DESCRIPTION** : PVC DOUBLE COATED HIGH TENACITY POLYESTER FABRIC

**COMPOSITION** : 82 % PVC  
18 % POLYESTER

**WIDTH** : 137 - 150 - 160 - 220 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.56	
TOTAL MASS (g/m <sup>2</sup> )	700 ± 60	EN ISO 2286-2
FABRIC MASS (g/m <sup>2</sup> )	130 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 250 T.: 140	EN ISO 1421
BREAKING EXTENSION (%)	L.: 18 T.: 18	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20.0 T.: 14.0	DIN 53363
COATING ADHESION (daN/50mm)	min. 5.0	EN ISO 2411
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
BURNING BEHAVIOUR	B1	DIN 4102

L - Along  
T - Across

**NOTE** : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2009.01.29	1		