



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: OPAKLIGHT FR

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER FABRIC

COMPOSITION : 83 % PVC
17 % POLYESTER

WIDTH : 137 - 150 - 160 - 202 - 220 - 320 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.43	
TOTAL MASS (g/m ²)	520 ± 40	EN ISO 2286-2
FABRIC MASS (g/m ²)	90 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 150 T.: 140	EN ISO 1421
BREAKING EXTENSION (%)	L.: 15 T.: 20	EN ISO 1421
TEAR STRENGTH (daN)	L.: 5.0 T.: 5.0	DIN 53363
COATING ADHESION (daN/50mm)	min 5.0	EN ISO 2411
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
BURNING BEHAVIOUR	M2	NF P92-503
BURNING BEHAVIOUR	B1	DIN 4102

L - Along
T - Across

NOTE : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2008.12.15	0		