



ENDUTEX - REVESTIMENTOS TEXTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: PRINT MS 74 FR

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER SCRIM

COMPOSITION : 57 % PVC
43 % POLYESTER

WIDTH : 160 – 250 -320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.37	
TOTAL MASS (g/m ²)	340 ± 30	EN ISO 2286-2
FABRIC MASS (g/m ²)	145 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 240 T.: 140	EN ISO 1421
BREAKING EXTENSION (%)	L.: 22 T.: 22	EN ISO 1421
TEAR STRENGTH (daN)	L.: 35 T.: 15	DIN 53363
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
AVERAGE PERMEABILITY OF FABRIC TO AIR (l/m ² /s)	1690	EN ISO 9237
AVERAGE LIGHT TRANSMISSION	22	SF 600 Plus Spectrophotometer
BURNING BEHAVIOUR	M2	NF P92-503
BURNING BEHAVIOUR	B1	DIN 4102
BURNING BEHAVIOUR	Pass	NFPA 701
OPEN AREA (%)	11	Internal

L – Along T – Across

NOTE : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2010.03.26	3		