



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



---

---

TECHNICAL DATA SHEET

---

---

**REFERENCE:** PRINT PA FL

**DESCRIPTION** : PVC DOUBLE COATED HIGH TENACITY POLYESTER FABRIC

**COMPOSITION** : 71 % PVC  
29 % POLYESTER

**WIDTH** : 137 - 150 - 160 - 202 - 220 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.42	
TOTAL MASS (g/m <sup>2</sup> )	450 ± 40	EN ISO 2286-2
FABRIC MASS (g/m <sup>2</sup> )	130 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 250 T.: 140	EN ISO 1421
BREAKING EXTENSION (%)	L.: 20 T.: 25	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20.0 T.: 15.0	DIN 53363
COATING ADHESION (daN/50mm)	min 5.0	EN ISO 2411
COLOUR FASTNESS TO LIGHT	See Note 2	EN ISO 105-B02
FLAMMABILITY (mm/min)	< 100	DIN 75200

L – Along T - Across

**NOTE 1** : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

**NOTE 2** : Fluorescent colors have poor light fastness. Particularly, in outdoor use, a discoloration will occur after a few weeks or a few months, depending on the degree of exposure to direct sunlight.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2009.09.02	0		